

ALCANTARA®

ALCANTARA® Avant

Cod. 5466

Application

Upholstery

Main Characteristics

COMPOSITION	ALCANTARA ® Backing	Polyester Polyurethane Cot/Kanecaron ®	68 ± 3 % 32 ± 3 % 45/55 %
FR CONTENT			(*) 28 ± 3 %
THICKNESS			≥ 0.95 mm
UNIT WEIGHT		EN 29073-1	530 ± 70 g/m2
WIDTH			≥ 142 cm
DIMENSIONAL STABILITY	Water 40°C	EN ISO 5077 + 6330	≤ 5 %
BREAKING LOAD	Lenghtwise Crosswise	EN ISO 13934-1	≥ 550 N ≥ 550 N
ELONGATION AT 50 N	Lenghtwise Crosswise	EN ISO 13934-1	≤ 5 % ≤ 15 %
TEAR STRENGTH	Lenghtwise Crosswise	EN ISO 13937-3	≥ 30 N
MARTINDALE ABRASION 12kPa	END POINT	EN ISO 12947-4 EN ISO 12947-2	(**) ≥ 30000 cycles ≥ 150000 cycles
COHESION	Alcantara-Backing	EN ISO 2411	≥ 8 N
SLIPPAGE RESISTANCE OF YARNS AT	Lenghtwise Crosswise	EN ISO 13936-2	≤ 6 mm
RESISTANCE TO PILLING	2000 cycles	EN ISO 12945-2	≥ 4/5
FLAME RESISTANCE		BS 5852 Crib 5 IMO RES A652 FAR/JAR 25.853	Complies

Color Fastness (***)

TO LIGHT	Xenotest Beta - 240h	UNI EN ISO 105 B02	≥ 5 blue scale (1-8)
TO DOMESTIC WASHING	Tone change Staining	UNI EN ISO 105 C06	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO DRY CLEANING	Tone change Staining	AATCC 132	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO RUBBING	Dry Wet	UNI EN ISO 105 X12	≥ 4 grey scale (1-5) ≥ 3 grey scale (1-5)
TO WATER	Tone change Staining	EN ISO 105 E01	≥ 4 grey scale (1-5) ≥ 3.5 grey scale (1-5)

General Washing



(*) Refeerd to Alcantara ®

(**) Slight change in the appearance of product surface

(***) Slight shade variations from one production batch to another one are possible on these products

Alcantara S.p.A. info@alcantara.com - www.alcantara.com Via Mecenate, 86 - 20138 Milano, Italy - Tel. +39 02 580301 - Fax. +39 02 58030460